HARDOX®
WEAR PLATE

Hardox® Round bar

General Product Description

The all-round abrasion-resistant steel as round bar.

Hardox® Round bars are versatile, ready-to-use, abrasion-resistant steels that combine high toughness and good weldability.

Hardox® Round bars come in diameters between 40 and 160 mm and lengths up to 5000 mm, and feature the same guaranteed properties as the wear plate. Delivered quenched or quenched and tempered to high tensile strength and hardness levels.

Hardox® round bars represent entirely new possibilities for stronger and lighter product design. They also help optimize workshop procedures such as machining and welding.

Mechanical Properties

Product	Diameter (mm)	Hardness [1] (HBW)
Hardox® 400	40.0 - 100.0	370 - 430
Hardox® 500	40.0 - 160.0	450 - 540

[1] Hardness is measured, according to EN ISO 6506-1, on a milled surface 12.5 mm below the ordered diameter. Bar hardness is measured on a milled surface, with indents positioned as impact test according to EN 10083.

Impact Properties

Product	Longitudinal test, typical impact energy, Charpy V 10x10 mm test specimen [1]	Min. impact energy for longitudinal testing, Charpy V 10x10 mm test specimen [1]
Hardox® 400	45 J / -40 °C	27 J / -40 °C
Hardox® 500	27 J / -20 °C	–

[1] Test specimen position according to EN 10083.

Chemical Composition (heat analysis)

Product	C *) (max %)	Si *) (max %)	Mn*) (max %)	P (max %)	S (max %)	Cr*) (max %)	Ni*) (max %)	Mo*) (max %)	B*) (max %)
Hardox® 400	0.32	0.70	1.60	0.025	0.010	2.50	1.50	0.60	0.004
Hardox® 500	0.30	0.40	1.30	0.020	0.010	2.80	2.0	0.40	0.005

The steel is grain refined. *) Intentional alloying elements.

Carbon Equivalent CET(CEV)

Product	Hardox® 400	Hardox® 500	Hardox® 500
Diameter (mm)	40.0 - 100.0	40.0 - 100.0	100.1 - 160.0
Max CET(CEV)	0.39 (0.60)	0.54 (0.95)	0.57 (1.13)
Typ CET(CEV)	0.37 (0.58)	0.46 (0.73)	0.48 (0.95)

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40} \qquad CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

SSAB

Tolerances

More details are given in SSAB's brochure Hardox® Guarantees or at www.ssab.com.

Bar Diameter

Tolerances for bar diameter are according to EN 10060 for Ø < 75 mm.
For Ø ≥ 75 mm, the tolerances are according to SSAB specification.

Length

Tolerances according to EN 10060.

Bar Straightness

Tolerances according to EN 10060.

Bar Surface

Black condition.

Delivery Conditions

The delivery condition is Quenched or Quenched and Tempered.

Delivery requirements can be found at www.ssab.com.

Fabrication and Other Recommendations

Welding, bending and machining

Recommendations can be found in SSABs brochures at www.hardox.com or consult Tech Support.

Hardox® Round bar is not intended for further heat treatment. It has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition cannot be retained after exposure to temperatures in excess of 250ºC.

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product. Grinding, especially of primer coated plates, may produce dust with a high particle concentration.

Contact Information

www.ssab.com/contact

The English version of this document shall prevail in case of discrepancy. Minor changes and updates to the document may occur, please download the latest version of this document at www.ssab.com

SSAB, Strenx, Hardox, Docol, GreenCoat, Toolox, Armox, Ramor, SSAB Domex, SSAB Laser, Raex, Duroxite are trademarks owned by the SSAB group of companies.